

<b>POLYCHEM 7014-BA-75</b>
----------------------------

**Polychem 7014-BA-75 (Z0766)**

Polychem 7014-BA-75 is an fast dry chain stopped alkyd. It dries in 5-10 min. to handle. It allows for formulation of low VOC coatings and has the added feature of responding to heated paint application for even lower viscosity.

CHARACTERISTICS	SPECIFICATIONS
Percent Non Volatile	75
Viscosity, G-H	Y-Z2
Acid Number	8 to 16
Gardner Color	8 Maximum
Weight Per Gallon	9.1 ± 0.1
Solvent	n Butyl Acetate
Modifier	?
Oil	Linseed Oil
Reduced Viscosity	A-B
Reduced NVM	50
Reduction Solvent	Xylene
Clarity	CLEAR TO SLIGHTLY HAZY
SUGGESTED USES	
General purpose industrial finishesPrimers	
DRIER RECOMMENDATIONS (% metal on total binder solids)	
Cobalt	0.03%Calcium
	0.03%Zircon
	0.25%

The information and specifications stated here are for the material currently offered, are subject to change without prior notice, and due to variations in user handling and application methods should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, express or implied, concerning this product or its use either singly or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user assures that workplace and disposal practices are in compliance with laws, regulations and ordinances. ALL WARRANTIES, INCLUDING WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE EXPRESSLY EXCLUDED. IN NO EVENT SHALL THE SUPPLIER BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES