

POLYCHEM 7520-M-60

Polychem 7520-M-60 (Z8130)

Polychem 7520-M-60 is an vinyl toluene modified linseed oil in a narrow cut aliphatic hydrocarbon, providing a flash point of greater than 100 degrees F, (combustible range), but at the same time allowing for faster dry than standard mineral spirit cuts. This product is low-HAP and can be formulated into HAP-free coatings (below 1% HAP).

| CHARACTERISTICS | SPECIFICATIONS |
|--|------------------------------|
| Percent Non Volatile | 60 |
| Viscosity, G-H | X-Z1 |
| Acid Number | 13 |
| Gardner Color | 7 Maximum |
| Weight Per Gallon | 7.45 ± 0.1 |
| Solvent | Quick Drying Mineral Spirits |
| Modifier | VT |
| Oil | Linseed Oil |
| Reduced Viscosity | D-E |
| Reduced NVM | 40 |
| Reduction Solvent | Quick Drying Mineral Spirits |
| Clarity | CLEAR TO SLIGHTLY HAZY |
| SUGGESTED USES | |
| Sanding sealers with improved open timeEquipment and metal furniture enamelsMiscellaneous fast air dry industrial or | |
| trade sale finishes | |
| DRIER RECOMMENDATIONS (% metal on total binder solids) | |
| Cobalt 0.01% | |

The information and specifications stated here are for the material currently offered, are subject to change without prior notice, and due to variations in user handling and application methods should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, express or implied, concerning this product or its use either singly or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user assures that workplace and disposal practices are in compliance with laws, regulations and ordinances. ALL WARRANTIES, INCLUDING WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE EXPRESSLY EXCLUDED. IN NO EVENT SHALL THE SUPPLIER BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES