

| |
|---------------------------|
| POLYCHEM 7565-B-60 |
|---------------------------|

Polychem 7565-B-60 (Z8265)

Polychem 7565-B-60 is an acrylic-VT modified alkyd, combining the fast dry properties of VT alkyds with improved durability. This resin is cut in a combination of mineral spirits and Solvent 100 to achieve a flashpoint of 100°F minimum.

| CHARACTERISTICS | SPECIFICATIONS |
|---|-------------------------------|
| Percent Non Volatile | 60 |
| Viscosity, G-H | Z2-Z4 |
| Acid Number | 8 |
| Gardner Color | 6 Maximum |
| Weight Per Gallon | 7.8 ± 0.1 |
| Solvent | Mineral Spirits/100 Solvent |
| Modifier | VT/ ACR |
| Oil | Soybean Oil |
| Reduced Viscosity | I-M |
| Reduced NVM | 40 |
| Reduction Solvent | Mineral Spirits, Low Aromatic |
| Clarity | CLEAR TO SLIGHTLY HAZY |
| SUGGESTED USES | |
| (not specified) | |
| DRIER RECOMMENDATIONS (% metal on total binder solids) | |
| Cobalt 0.05%Calcium 0.03%Zirconium 0.50% | |

The information and specifications stated here are for the material currently offered, are subject to change without prior notice, and due to variations in user handling and application methods should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, express or implied, concerning this product or its use either singly or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user assures that workplace and disposal practices are in compliance with laws, regulations and ordinances. ALL WARRANTIES, INCLUDING WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE EXPRESSLY EXCLUDED. IN NO EVENT SHALL THE SUPPLIER BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES