

POLYCHEM 7635-T-BA-60

Polychem 7635-T-BA-60 (Z8747)

Polychem 7635-T-BA-60 is an short linseed/rosin/phenolic modified oxidizing alkyd which offers lift resistance and fast dry. This is the same as OPC 7348-X-50 but reduced in t-Butyl Acetate.

CHARACTERISTICS	SPECIFICATIONS
Percent Non Volatile	60
Viscosity, G-H	Z-Z2
Acid Number	15 to 25
Gardner Color	12 Maximum
Weight Per Gallon	8.5 ± 0.1
Solvent	t-Butyl Acetate
Modifier	Phenolic/ Rosin
Oil	Linseed Oil/TUNG Oil
Reduced Viscosity	P-S
Reduced NVM	50
Reduction Solvent	t-Butyl Acetate
Clarity	10 max
SUGGESTED USES	
Primers and surfacersFast drying enamels	
DRIER RECOMMENDATIONS (% metal on total binder solids)	
Cobalt	0.03%Dri RX 0.20%

The information and specifications stated here are for the material currently offered, are subject to change without prior notice, and due to variations in user handling and application methods should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, express or implied, concerning this product or its use either singly or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user assures that workplace and disposal practices are in compliance with laws, regulations and ordinances. ALL WARRANTIES, INCLUDING WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE EXPRESSLY EXCLUDED. IN NO EVENT SHALL THE SUPPLIER BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES