

POLYCHEM G2507-OMS-70

Polychem G2507-OMS-70 (Z2033)

Polychem G2507-OMS-70 is an general purpose gloss air drying enamel vehicle with excellent resistance to yellowing on aging. This resin is designed for use in enamels where low V.O.C. is required.

CHARACTERISTICS	SPECIFICATIONS
Percent Non Volatile	70
Viscosity, G-H	Z3-Z5
Acid Number	14
Gardner Color	8 Maximum
Weight Per Gallon	8 ± 0.1
Solvent	Odorless Mineral Spirits
Modifier	?
Oil	Soybean Oil
Reduced Viscosity	G-K
Reduced NVM	50
Reduction Solvent	Odorless Mineral Spirits
Clarity	Clear
SUGGESTED USES	
Used for high quality exterior gloss and trim enamels. Also used in many industrial finishes such as machinery enamels, freight and marine paints, etc.	
DRIER RECOMMENDATIONS (% metal on total binder solids)	
Air Dry: 25 C, 50% RH, 0.075 mm Wet Touch Dry Tack Free 5-6 hrs.Driers:	
Cobalt 0.06% Calcium 0.1%	

The information and specifications stated here are for the material currently offered, are subject to change without prior notice, and due to variations in user handling and application methods should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, express or implied, concerning this product or its use either singly or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user assures that workplace and disposal practices are in compliance with laws, regulations and ordinances. ALL WARRANTIES, INCLUDING WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE EXPRESSLY EXCLUDED. IN NO EVENT SHALL THE SUPPLIER BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES