

POLYCHEM G2509HV-MS16-50

Polychem G2509HV-MS16-50 (Z2040)

Polychem G2509HV-MS16-50 is an glyptal medium oil Soya alkyd. It is a general-purpose vehicle for brushing or spraying enamels or primers.

CHARACTERISTICS	SPECIFICATIONS
Percent Non Volatile	50
Viscosity, G-H	Z3-Z4
Acid Number	12
Gardner Color	7 Maximum
Weight Per Gallon	7.66 ± 0.1
Solvent	MS-16
Modifier	?
Oil	Soybean Oil
Reduced Viscosity	M-Q
Reduced NVM	40
Reduction Solvent	MS-16
Clarity	Clear
SUGGESTED USES	
Used for light color applications, low bake applications and dipping enamels	
DRIER RECOMMENDATIONS (% metal on total binder solids)	
Air Dry: 25 C, 50% RH, 0.075 mm Wet Touch Dry Tack Free 4-6 hrs.	
HardDriers: Cobalt 0.04% Calcium 0.1%	

The information and specifications stated here are for the material currently offered, are subject to change without prior notice, and due to variations in user handling and application methods should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, express or implied, concerning this product or its use either singly or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user assures that workplace and disposal practices are in compliance with laws, regulations and ordinances. ALL WARRANTIES, INCLUDING WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE EXPRESSLY EXCLUDED. IN NO EVENT SHALL THE SUPPLIER BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES