

POLYCHEM G7764-X-60

Polychem G7764-X-60 (Z2129)

Polychem G7764-X-60 is a product with good durability, excellent adhesion, good gloss retention and abrasion resistance. It is a fast air drying and baking vehicle.

CHARACTERISTICS	SPECIFICATIONS
Percent Non Volatile	60
Viscosity, G-H	Z2-Z4
Acid Number	16 to 25
Gardner Color	9 Maximum
Weight Per Gallon	8.45 ± 0.1
Solvent	Xylene
Modifier	?
Oil	Linseed Oil
Reduced Viscosity	P-U
Reduced NVM	50
Reduction Solvent	Xylene
Clarity	CLEAR
SUGGESTED USES	
Used in metal primers, implement enamels, lacquer primers, and automotive primers.	
DRIER RECOMMENDATIONS (% metal on total binder solids)	
Air Dry: 25 C, 50% RH, 0.075 mm Wet	Touch Dry Tack Free HardDriers:
Cobalt 0.02% Calcium 0.2% Zirconium 0.1%	

The information and specifications stated here are for the material currently offered, are subject to change without prior notice, and due to variations in user handling and application methods should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, express or implied, concerning this product or its use either singly or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user assures that workplace and disposal practices are in compliance with laws, regulations and ordinances. ALL WARRANTIES, INCLUDING WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE EXPRESSLY EXCLUDED. IN NO EVENT SHALL THE SUPPLIER BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES