

<b>POLYCHEM G7800-V-50</b>
----------------------------

Polychem G7800-V-50 (Z2170)

Polychem G7800-V-50 is an glyptal paint traffic alkyd. It has excellent bleed resistance, rapid set up and good performance.

CHARACTERISTICS	SPECIFICATIONS
Percent Non Volatile	50
Viscosity, G-H	Z4-Z6
Acid Number	12
Gardner Color	7 Maximum
Weight Per Gallon	7.5 ± 0.1
Solvent	VM&P
Modifier	?
Oil	Linseed Oil / Soybean Oil
Reduced Viscosity	R-V
Reduced NVM	40
Reduction Solvent	VM&P
Clarity	CLEAR
SUGGESTED USES	
Used for traffic paints or industrial primers and fast evaporating enamels.	
DRIER RECOMMENDATIONS (% metal on total binder solids)	
Air Dry: 25 C, 50% RH, 0.075 mm Wet	Touch Dry 3-5 Minutes Tack Free
4-5 Hours HardDriers Cobalt 0.04% Calcium 0.2%	

The information and specifications stated here are for the material currently offered, are subject to change without prior notice, and due to variations in user handling and application methods should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, express or implied, concerning this product or its use either singly or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user assures that workplace and disposal practices are in compliance with laws, regulations and ordinances. ALL WARRANTIES, INCLUDING WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE EXPRESSLY EXCLUDED. IN NO EVENT SHALL THE SUPPLIER BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES